

## PROCLAD150™ - Colors

### The Professional Cladding System

#### Product Description

PROCLAD150™ is the premium multi-layered laminate system, which provides a weatherproof cladding and jacketing system to insulated duct and pipe systems. The 6-ply laminate has a zero-perm rating to prevent moisture ingress and with increased strength and UV resistance, PROCLAD150™ provides a market leading solution. The technically advanced adhesive being solvent free for safe environmentally conscious use, is capable of being applied in wet/humid conditions at extremes of temperatures (-22°F to +266°F).

#### Characteristics & Advantages

- External & internal applications
- Proven UV resistance, 10 years+
- Increased puncture resistance
- Salt water resistant
- Resistant to a range of chemicals
- Compliant for direct food contact
- 15/35 ASTM E84 / UL723 rated
- Approved by FDA & CFIA for indirect food contact
- Extends the serviceable life of infrastructure and lowers maintenance costs

#### Product Data

Item	Value	Standard
<b>Product Thickness</b>	7.08 mils	
<b>Tensile Strength</b>	67 lb/in	EN 527-3
<b>Elongation</b>	>60%	EN 527-3
<b>Water Permeability</b>	0.00 g/m <sup>2</sup> /d	ASTM F1249 ISO 15106-2
<b>Puncture Resistance</b>	35 lbs	DIN EN 14477
<b>Service Temperature</b>	-40°F to +284°F	
<b>Application Temperature</b>	-22°F to +266°F	
<b>Emissivity Value</b>	0.84 to 0.95	
<b>UV Testing</b>	10 years plus	ASTM G 26A ISO 4892-2
<b>Fire Rating</b>	15/35	ASTM E84 / UL723

#### Product Range & Sizes

Name	Colour	Mils	Width (inches)	Length(yards)
<b>PROCLAD 150B</b>	Black	7.08 mils	24, 36† & 47†	55
<b>PROCLAD 150G</b>	Grey	7.08 mils	24, 36† & 47†	55
<b>PROCLAD 150W</b>	White	7.08 mils	24, 36† & 47†	55

†Available in both adhesive and non-adhesive form.

#### Installation Guidelines

<b>Coverage</b>	1 x 24 inch roll equates to 35.7 yd <sup>2</sup> 1 x 36 inch roll equates to 55 yd <sup>2</sup> 1 x 47 inch roll equates to 71.8 yd <sup>2</sup>
-----------------	--



# Technical Data Sheet

**Surface preparation:** Ensure all surfaces are dry and clean, free from dirt and dust, grease, oil and silicones. The insulation materials should be installed to industry standards and sealed using one of ProTech Global's aluminum foil tapes, GT50HT™ or GT1625HT™.

**Application:** When applying PROCLAD150™ ensure that the correct pressure is applied using the plastic applicator (provided) as the adhesive is a PSA and requires a firm application to provide a full surface bond.

When placing the cut piece of PROCLAD150™ in to position, partially peel back the liner to allow correct positioning and then rub down, continue to peel back the liner whilst pressing in to place using the hand to prevent creasing, once the full piece has been applied use the plastic applicator and rub the complete surface to ensure the full adhesive bond required.

Continue to apply PROCLAD150™ ensuring that a minimum 3-inch overlap is observed to the previous piece to ensure a strong weatherproof seal.

**Method Statements:** ProTech Global Ltd provides detailed method statements for use in various applications, and are available upon request. These must be referred to prior to commencing work.

## Alternative Products

PROCLAD350™ provides a market leading solution, with increased durability and unique memory effect which helps to absorb impacts without deformation or damage providing long term performance and excellent appearance.

## Proclad150™ Weather Protection Cover Film – Physical & Chemical Stability

<b>Acids</b>	acetic acid (all concentrations)	resistant
	50% formic acid	resistant
	10% hydrochloric acid	resistant
	30% hydrochloric acid	partially resistant
	10% and 25% hydrofluoric acid	resistant
	10% nitric acid	resistant
	65% and 100% nitric acid	not resistant
	30% and 85% phosphoric acid	resistant
	20% sulphuric acid	partially resistant
	sulphur dioxide gas, dry	resistant
80% and above sulphuric acid	not resistant	
<b>Aldehydes</b>	acetaldehyde	resistant
	formaldehyde	resistant
<b>Alcohols</b>	benzyl alcohol	partially resistant
	cyclohexanol	resistant
	ethyl alcohol	resistant
	glycerine	resistant
	glycol	resistant

# Technical Data Sheet

	isopropyl alcohol	resistant
	methyl alcohol	resistant
<b>Aqueous alkaline solutions</b>	ammonium hydroxide	not resistant
	calcium hydroxide	partially resistant
	sodium hydroxide	not resistant
<b>Chlorinated hydrocarbons</b>	carbon tetrachloride	partially resistant
	chlorinated biphenyls	partially resistant
	chloroform	resistant
	trichloroethylene	resistant
<b>Esters</b>	ethyl acetate	resistant
<b>Hydrocarbons</b>	aliphatic hydrocarbons	resistant
	benzene	resistant
	gasoline (petrol)	resistant
	mineral oils	resistant
	toluene	resistant
	xylene	resistant
<b>Miscellaneous substances</b>	Calcium hypochlorite	resistant
	chlorine	resistant
	hydrogen peroxide	resistant
	oxygen	resistant
	Sodium hypochlorite	resistant
	water*	resistant
<b>Other organic solutions</b>	acetone	resistant
	diethylether	resistant
	nitrobenzene	not resistant
	phenol	not resistant
<b>Salt solutions</b>	alkaline carbonates	resistant
	bichromates	resistant
	cyanides	resistant
	fluorides	resistant
	Sodium Chloride	resistant

\*At elevated temperatures (approx. > 212°F) and in the presence of water (vapour), the PROCLAD150™ cover film tends to become brittle as a result of hydrolysis.



# Technical Data Sheet

## Legal Notices

---

The information, and, in particular, the recommendations relating to the application and end-use of ProTech Global Ltd products, are given in good faith based on ProTech Global Ltd.'s current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with ProTech Global Ltd.'s recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. ProTech Global Ltd reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---

## About ProTech Global Ltd

ProTech Global Ltd is a UK based company that has manufactured anti-corrosion products for over 25 years. With many years' experience in differing types of protection scenarios, ProTech Global Ltd has a reputation as a trusted supplier and partners with many corporations worldwide.

**ProTech Global Ltd:**

**Unit 1 Manor Farm, Green Lane, Failand, Bristol, BS8 3TP, UK**

**Tel:+44 (0)117 298 0573**

**Email: [sales@protechglobal.co.uk](mailto:sales@protechglobal.co.uk)**